

(19) World Intellectual Property Organization  
International Bureau(43) International Publication Date  
3 January 2002 (03.01.2002)

PCT

(10) International Publication Number  
WO 02/00812 A2

- (51) International Patent Classification: C10L (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (21) International Application Number: PCT/GB01/02911
- (22) International Filing Date: 29 June 2001 (29.06.2001)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:  
0016032.5 29 June 2000 (29.06.2000) GB  
0022449.3 13 September 2000 (13.09.2000) GB
- (71) Applicant (for all designated States except US): CELOX LIMITED [GB/GB]; P.O. Box 4260, Poole BH13 7YS (GB).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): HAZARIKA, Ronen [GB/GB]; P.O. Box 4260, Poole BH13 7YS (GB). MORGAN, Bryan, Lawrence [GB/GB]; P.O. Box 4260, Poole BH13 7YS (GB).
- (74) Agents: FISHER, Adrian, John et al.; Carpmals & Ransford, 43 Bloomsbury Square, London WC1A 2RA (GB).
- Published:**  
— without international search report and to be republished upon receipt of that report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

WO 02/00812 A2

(54) Title: A FUEL ADDITIVE

(57) Abstract: This invention relates to a method for improving the efficiency with which fuel is burnt in a fuel burning apparatus, particularly an internal combustion engine, comprising dispersing an amount of at least one particulate lanthanide oxide, particularly cerium oxide, in the fuel. This invention further relates to tablets, capsules, compositions and liquid fuel additives suitable for dispersing a lanthanide oxide in fuel.

A FUEL ADDITIVE

This invention relates to a method for improving the efficiency of combustion processes and/or reducing harmful emissions. This invention further relates to a composition, tablet, capsule or liquid fuel additive suitable for dispersing a lanthanide (rare earth) oxide in a fuel.

Lanthanide compounds, particularly organometallic compounds of cerium, are known to be useful additives in fuel because they aid combustion. It is believed that these compounds adsorb onto the asphaltenes always present in fuel oil. During the combustion process, metal oxides are formed and, because of the catalytic effect of rare earth oxides on the combustion of asphaltenes, they reduce the quantity of solid unburned components released during combustion. Hence, organometallic lanthanide additives in fuel have an effect on improving combustion and reducing harmful emissions.

Several documents in the prior art describe the use of lanthanide compounds as fuel additives. For example, French patent 2,172,797 describes organic acid salts prepared from rare earths, particularly from cerium, which are useful as combustion aids. The use of organic acid salts of rare earth compounds was necessary since these compounds were found to be soluble in fuels.

US patent 4,264,335 describes the use of cerium 2-ethylhexanoate for suppressing the octane requirement of a gasoline-fired internal combustion engine. Cerium 2-ethylhexanoate was found to be more soluble in gasoline than cerium octanoate.

US patent 5,240,896 describes the use of a ceramic material containing a rare earth oxide. The ceramic material is insoluble in fuel. It is alleged that combustion of the liquid fuel is accelerated upon contact with the solid ceramic.

European patent 0485551 describes a device which conveys dry particles of a rare earth oxide directly to the combustion chamber of an internal combustion engine via the air intake.

In general, the fuel additives described in the prior art employ organic acid salts of rare earth elements, which are soluble in fuel. It is believed that these compounds are converted to rare earth oxides in the combustion chamber. Thus, the rare earth oxides are the active catalytic compounds.

5

Organic acid salts of lanthanides such as cerium are generally highly viscous liquids or low melting point solids. These compounds are inherently difficult to introduce into fuel in a convenient manner. Furthermore, such materials are expensive to manufacture and difficult to handle.

10

Although lanthanide oxides can be bought in large quantities at a relatively low cost, these compounds are not considered to be suitable for use in fuels for internal combustion engines. In general, it is desirable to avoid having particulate matter dispersed in the fuel system and in the combustion chamber of an internal combustion engine. Particulate materials are known to block fuel filters and also act as abrasive agents which have harmful effects on the pistons and combustion chamber of the engine. Cerium oxide is a particularly well known abrasive agent.

It is an object of the present invention to provide a method for improving the combustion efficiency of, for example, an internal combustion engine, which is less costly and more convenient than methods that are described in the prior art.

Accordingly, the present invention provides a method of improving the efficiency with which fuel is burnt in a fuel burning apparatus and/or a method of reducing the emissions produced by a fuel which is burnt in a fuel burning apparatus, said method comprising dispersing an amount of at least one particulate lanthanide oxide in the fuel.

When the method of the present of invention is employed, the fuel burning apparatus may be, for example, a boiler, furnace, jet engine or internal combustion engine. A fuel which contains a dispersion of the lanthanide oxide as hereinbefore described is delivered to the combustion chamber of an internal combustion engine or fire box or nozzle head of a burner unit. Preferably, the fuel burning apparatus is an internal combustion engine. The internal combustion engine may be of any type including spark ignition engines and

compression ignition engines. Similarly, the fuel may be of any type, including petrol/gasoline (both leaded and unleaded), diesel and LPG (liquid petroleum gas) fuel.

- When the method of the present invention is used, particularly in an internal combustion engine, the amount of harmful pollutants is reduced. These pollutants include, for example, CO, CO<sub>2</sub>, hydrocarbons (HCs) and NO<sub>x</sub>. The reduction in the amount of harmful pollutants may obviate the need for a catalytic converter in some vehicles. Moreover, the reduction in the amount of harmful pollutants may be effected at a significantly lower cost using the method of the present invention as compared to, for example, the use of a catalytic converter, which requires precious metals such as rhodium, platinum and palladium.

- Furthermore, the method of the present invention improves combustion efficiency in, for example, an internal combustion engine ("engine"). Accordingly, an engine will benefit from reduced carbon build up in injectors and combustion chambers, an increase in power and torque, a reduction in engine wear, a reduction in fuel consumption and a reduction in the number of partial misfires which occur in most engines. Additional benefits include a decrease in lubrication oil consumption and extended oil life. When present, catalytic converter life is also extended due to the reduction of unburned hydrocarbons entering the catalyst and also a recharging of the catalyst through lanthanide oxide deposits.

- It is an important advantage of the method of the present invention that it can be applied to existing vehicles, even vehicles driven by engines which use unleaded fuel. Moreover, vehicles that are unable to use unleaded fuel due to soft valve seats will be able to use unleaded fuel by employing the method of the present invention. Cerium oxide, for example, in the fuel will provide the same protective properties as tetraethyl lead in preventing valve seat recession. In addition, cerium oxide can suppress the octane requirement of an engine, acting as an octane improver.

- As used herein, the term "lanthanide" includes any of the rare earth elements; that is any element from atomic number 58 to 71, and also including scandium, yttrium and lanthanum.

Preferably, the lanthanide oxide comprises a lanthanide selected from cerium, lanthanum, neodymium and praseodymium. Preferably, the lanthanide oxide is  $\text{CeO}_2$ .

As used herein, the term "dispersion" means a persistent suspension or emulsion of solid  
5 particles in a liquid medium, or a solution of a solid dissolved in a liquid medium. The term "dispersion" does not include a liquid comprising solid particles which initially disperse, but then settle out.

The particulate nature of the lanthanide oxide facilitates its dispersion in fuel. The particles  
10 of lanthanide oxide added to the fuel are discrete particles, rather than aggregates. Hence, the term "particle size" as used herein refers to the primary particle size. Preferably, the mean particle size of the lanthanide oxide is in the range of 1 nm to 100 microns. More preferably, the mean particle size is in the range of 1 nm to 5 microns, more preferably 1 nm to 0.5 microns, more preferably 1 nm to 50 nm, and more preferably 1 nm to 10 nm.

15 The particle size of the lanthanide oxide affects the extent to which the compound is dispersed in fuel. In general, a small mean particle size (less than 5 microns) is preferred since small particles are usually more readily dispersed in fuels than large particles.

20 The particles of lanthanide oxide may be produced by methods known in the art, such as mechanical grinding. The grinder may impart a high frequency, low amplitude vibration to the lanthanide oxide as it is ground. Other suitable methods known in the art include vapour condensation, combustion synthesis, thermochemical synthesis, sol-gel processing and chemical precipitation. Preferred methods for producing particles of lanthanide oxide  
25 are mechanical chemical processing (see US 6,203,768) and plasma vapour synthesis (see US 5,874,684, US 5,514,349 and US 5,460,701).

Preferably, the particles are generally spheroidal.

30 The particle size of the lanthanide oxide may be measured by any convenient method, such as laser diffraction analysis or ultrasonic spectrometry.

The amount of lanthanide oxide required will depend on the total surface area of the lanthanide oxide particles and also fuel tank capacity. Accordingly, the smaller the particle size, the smaller the amount of lanthanide oxide required, since smaller particles have a higher ratio of surface area to volume and have enhanced catalytic abilities due to their highly stressed surface atoms which are extremely reactive. Preferably, the particles of lanthanide oxide have a surface area of at least about 20 m<sup>2</sup>/g, more preferably at least about 50 m<sup>2</sup>/g, and more preferably at least about 80 m<sup>2</sup>/g. Preferably, the amount of lanthanide oxide added to the fuel is such that its concentration is in range of 0.1 to 400 ppm. More preferably, the concentration of lanthanide oxide is in the range of 0.1 to 100 ppm, more preferably 1 to 50 ppm, and more preferably 1 to 10 ppm.

It has been found that particles of cerium oxide produced by plasma vapour synthesis retain their high surface area at high temperature. By high temperature, it is meant the typical combustion temperature of an internal combustion engine. Generally, surface area tends to decrease at high temperature in most particles. However, it is a further advantage of the present invention that the particles of cerium oxide produced by plasma vapour synthesis or mechanical chemical processing do not lose surface area at high temperature. This allows them to be used at concentrations as low as 1 to 10 ppm.

In one embodiment of the present invention, the lanthanide oxide is coated with a substance which renders the surface of the lanthanide compound lipophilic. The lipophilic coating aids dispersion of lanthanide oxides in fuels and also helps to prevent agglomeration of the particles. In some cases, the lipophilic coating allows complete solubilisation of the lanthanide oxide in fuel. The lipophilic coating also prevents the particles of lanthanide oxide from reacting with the fuel during storage in a fuel tank. Reaction of the lanthanide oxide and the fuel during storage is highly undesirable, since it leaves solid deposits in the fuel.

The particles may be coated by any suitable coating method known in the art. Suitable coating methods are described in US 5,993,967 and US 6,033,781.

The substance used to coat the surface of the lanthanide oxide is preferably a surfactant. The lipophobic part of the surfactant molecule is embedded into the lanthanide oxide particle, leaving the lipophilic part of the surfactant to interact with the fuel.

- 5 Preferably, the surfactant has a low HLB (hydrophilic/lipophilic balance). Surfactants having a low HLB are generally more oil soluble than those surfactants having a high HLB. Suitable low HLB surfactants will be readily apparent to the person skilled in the art. Preferably, the HLB of the surfactant is 7 or less, more preferably 4 or less. Examples of low HLB surfactants are alkyl carboxylic acids, anhydrides and esters having at least one
- 10 C<sub>10</sub>-C<sub>30</sub> alkyl group, such as dodecenyl succinic anhydride (DDSA), stearic acid, oleic acid, sorbitan tristearate and glycerol monostearate. Other examples of low HLB surfactants are hydroxyalkyl carboxylic acids and esters having at least one C<sub>10</sub>-C<sub>30</sub> hydroxyalkyl group, such as Lubrizol® OS11211. More preferably, the substance used to coat the lanthanide oxide is dodecenyl succinic anhydride (DDSA) or oleic acid.

15

In this embodiment of the present invention, the coated particles of lanthanide oxide dispersed in the fuel break down immediately upon entering the combustion chamber of an internal combustion engine. The lipophilic coating decomposes quickly in the combustion chamber, so ensuring that the catalytic activity of the lanthanide oxide is not harmed.

20

- In the method of the present invention other materials may be added to the fuel in addition to the lanthanide oxide. These other materials should all disperse in fuel and not interfere with the combustion process or block filters. Suitable materials include alternative combustion aids that are well known in the art. Examples of alternative combustion aids
- 25 include compounds of manganese, iron, cobalt, nickel, barium, strontium, calcium and lithium. Such combustion aids are described in US Patents 6,096,104 and 4,568,360, the contents of which are incorporated herein by reference.

- In addition, compounds such as fragrances may also be added to the fuel in the method of
- 30 the present invention. Examples of suitable fragrances are jasmine oil, vanilla oil and eucalyptus oil.

Preferably, the fuel is one suitable for use in an internal combustion engine. Examples of such fuels include petrol/gasoline, diesel or LPG (liquid petroleum gas) fuel.

- In a further aspect of the present invention, there is provided a tablet suitable for dispersion
- 5 of at least one lanthanide oxide in fuel comprising at least one lanthanide oxide as hereinbefore described and at least one tableting aid which is dispersible in the fuel. The term "tablet" as used herein has its usual meaning of a solid tablet of a compressed material.
- 10 Known methods for tableting are principally directed to water-soluble pharmaceuticals. Such methods are well known in the art and are exemplified by the use of tableting aids such as cellulose, lactose, silica, polyvinylpyrrolidone and citric acid. These and other tableting aids are described in, for example, US Patents 5,840,769 and 5,137,730.
- 15 However, these known tableting aids are unsuitable for preparing lanthanide oxide tablets which are dispersible in fuel. The use of binders such as magnesium stearate, methyl cellulose or silica produces tablets which either do not disperse in fuel, or tablets in which the binder(s) settle out after the tablet has dispersed in the fuel. Such tablets are unsuitable for use as fuel additives since the solid deposits block filters or build up on pistons and
- 20 combustion chambers.

Preferably, the tableting aid used in the tablet of this aspect of the present invention is a C<sub>7</sub>-C<sub>30</sub> alkyl carboxylic acid, a C<sub>6</sub>-C<sub>30</sub> aromatic compound or a polymeric tableting aid. More preferably, the tableting aid is tetradecanoic acid.

- 25 When the tableting aid is polymeric, polymers or copolymers of styrene, C<sub>1</sub>-C<sub>6</sub> alkyl-substituted styrenes and C<sub>1</sub>-C<sub>6</sub> alkyl methacrylates are preferred. More preferably, the polymeric tableting aid is poly(*t*-butylstyrene), poly(isobutyl methacrylate) or poly(*n*-butyl methacrylate).
- 30 As used herein, the term "alkyl" means a branched or unbranched, cyclic or acyclic, saturated or unsaturated (e.g. alkenyl or alkynyl) hydrocarbyl radical.



As used herein, the term "aromatic compound" means an aromatic hydrocarbon compound, such as benzene or naphthalene, optionally substituted with one or more C<sub>1</sub>-C<sub>6</sub> alkyl group(s). An example of a substituted aromatic compound suitable for use as a tableting aid in the present invention is durene (1,2,4,5-tetramethylbenzene).

5

Preferably, the amount of lanthanide oxide in the tablet of the present invention is in the range of 1 to 99.99 wt. %, based on the total weight of the tablet. More preferably, the amount of lanthanide oxide is in the range of 30 to 80 wt. % and more preferably 40 to 60 wt. %. More preferably, the amount of lanthanide oxide in the tablet is about 50 wt. %.

10

Preferably, the amount of tableting aid in the tablet of the present invention is in the range of 0.01 to 99 wt. %, based on the total weight of the tablet. More preferably, the amount of tableting aid is in the range of 20 to 70 wt. % and more preferably 40 to 60 wt. %. More preferably, the amount of tableting aid in the tablet is about 50 wt. %.

15

The tablet of the present invention may be obtained by application of a direct compression force to a composition comprising a lanthanide oxide as hereinbefore described and a tableting aid as hereinbefore described. When the tablet is obtained by direct compression, single stroke presses or rotary head presses may be employed. Alternatively, the tablet may be obtained by injection moulding or normal die moulding. These and other methods of tableting will be well known to the person skilled in the art. Generally, it is desirable to maximise the amount of lanthanide oxide in the tablet, whilst still being able to form tablets from the composition.

20

25 In an alternative embodiment of the present invention, there is provided a capsule suitable for dispersion of at least one lanthanide oxide in fuel, the tablet comprising an outer case and a substance contained therein, wherein the outer case comprises at least one tableting aid as hereinbefore described and the substance contained therein comprises at least one lanthanide oxide.

30

Capsules are well known for the delivery of, for example, pharmaceuticals. Generally, the outer case has two parts which engage to enclose the substance contained therein. The outer case should generally be dispersible to allow the release of the substance contained

therein into a liquid medium. Accordingly, in the present invention, the outer case of the capsule is dispersible in fuel, such as fuel for internal combustion engines.

- In a further embodiment of the present invention, there is provided a liquid fuel additive  
5 suitable for dispersion of at least one lanthanide oxide in fuel, comprising a dispersion of at least one coated lanthanide oxide as hereinbefore described in an organic liquid medium. Preferably, the lanthanide oxide is coated with a lipophilic coating as hereinbefore described, such as DDSA or oleic acid. The liquid fuel additive may be blended into bulk supplies of fuel or provided in the form of a one shot liquid additive to be added, for  
10 example, to the fuel tank of a vehicle. The liquid fuel additive may additionally comprise stabilising surfactants such as the low HLB surfactants described hereinbefore.

- Accordingly, the lanthanide oxide may be in the form of a loose powder, tablet, capsule or liquid fuel additive. These may be dispensed into fuels manually (e.g. by addition to the  
15 fuel tank at the time of refuelling) or with the aid of a suitable mechanical or electrical dosing device that may be utilised to automatically dose an appropriate amount of lanthanide oxide into the fuel.

- This invention further relates to an apparatus comprising an internal combustion engine  
20 and a fuel system, wherein said fuel system comprises a fuel tank containing fuel, and means for delivering said fuel from said fuel tank to said internal combustion engine, characterised in that said fuel has at least one lanthanide oxide dispersed therein. Preferably, the apparatus is a ship, aeroplane or motor vehicle, such as a motor car (automobile), lorry or motor cycle.

- 25 Specific embodiments of the present invention are now described by way of example only.

#### Example 1

- 30 A tablet was prepared from cerium oxide and tetradecanoic acid by direct compression. The amount of cerium oxide in the tablet was 60 wt. %. The amount of tetradecanoic acid in the tablet was 40 wt. %. The particle size of cerium oxide was about 0.3  $\mu\text{m}$ . This particle size gives a surface area of approximately 20  $\text{m}^2$  per gram, as measured by a

standard nitrogen adsorption method. The cerium oxide was prepared by mechanical grinding.

The tablet was added to the fuel tank of a 1988 Metro 1300 cc car, running on unleaded petrol, to give a concentration of about 30 ppm of cerium oxide in the fuel.

In normal operation of the vehicle, fuel consumption was reduced by about 40%. In addition, the use of the choke was greatly reduced and the overall performance of the vehicle was drastically improved.

10

#### Example 2

A tablet was prepared according to Example 1. The tablet was added to the fuel tank of a 1990 petrol Ford Transit, running on unleaded fuel, to give a concentration of about 30 ppm of cerium oxide in the fuel. Before addition of the tablet, the engine of the vehicle was known to suffer from pinking.

After 10 miles of normal operation, the pinking had been eradicated. In addition, performance of the vehicle had improved markedly.

20

#### Example 3

A tablet was prepared according to Example 1. The tablet was added to the fuel tank of a 1987 Mercedes 300E 2.8L, running on unleaded fuel, to give a concentration of about 30 ppm of cerium oxide in the fuel.

Before addition of the tablet, the following emission levels were measured from the exhaust:

CO - 0.15%, Hydrocarbons - 211 ppm, CO<sub>2</sub> - 14.37%.

After addition of the tablet, the following emission levels were measured:

CO - 0.01%, Hydrocarbons - 50 ppm, CO<sub>2</sub> - 13.97%.

#### Example 4

- 5 Cerium oxide particles were coated with stearic acid. A tablet was prepared from the coated cerium oxide particles and poly(isobutyl methacrylate) by die moulding. The amount of coated cerium oxide particles in the tablet was 30 wt. %. The amount of poly(isobutyl methacrylate) in the tablet was 70 wt. %. The particle size of cerium oxide was about 0.3  $\mu\text{m}$ . This particle size gives a surface area of approximately 20 m<sup>2</sup> per gram, as measured by a standard nitrogen adsorption method. The cerium oxide was prepared by mechanical grinding.

- The tablet was added to the fuel tank of a 1986 Ford Sierra 1.8L giving a concentration of 30 ppm of cerium oxide in the fuel. The vehicle was previously using leaded fuel and was not specially adapted for the use of unleaded fuel.

- The vehicle was able to use unleaded fuel without any observable problems after addition of the cerium oxide tablet. Furthermore, the performance and fuel economy of the vehicle were increased. In addition, more torque was available when towing a caravan.

20

#### Example 5

- A tablet was prepared according to Example 4. The tablet was used in a 1997 Ford Scorpio, running on unleaded fuel, at a concentration of 30 ppm of cerium oxide.

25

- The fuel economy of the vehicle was increased by 10-12% and the performance of the vehicle was noticeably improved.

#### Example 6

30

- Cerium oxide coated with DDSA was added to diesel fuel at a concentration of 4 ppm. The mean particle size of cerium oxide prior to coating was 10 nm. This particle size gives a surface area of approximately 80 m<sup>2</sup> per gram, as measured by a standard nitrogen

adsorption method. The particles were made by plasma vapour synthesis. The fuel was used on a static diesel engine coupled to a dynamometer and smoke emission equipment. After adding the dosed fuel, increased torque and power was observed. In addition, smoke opacity was reduced to zero between 1000 and 2000 rpm. At 2000 to 2500 rpm, smoke was  
5 reduced by 30%.

#### Example 7

Cerium oxide coated with DDSA was added to the fuel of a 1998 Jaguar S type 3.0 vehicle  
10 at a concentration of 4 ppm. The particle size of cerium oxide prior to coating was 5 nm. This particle size gives a surface area of approximately  $150 \text{ m}^2$  per gram, as measured by a standard nitrogen adsorption method. The particles were made by plasma vapour synthesis. Average fuel economy increased from 27.1 mpg to 30.5 mpg after the coated cerium oxide had been added to the fuel.

15

The above examples clearly demonstrate that the addition of a lanthanide oxide according to the present invention to the fuel of vehicles improves their performance, reduces pinking and reduces emissions. In addition, no blocking of filters or excessive piston wear was observed.

20

It will, of course, be understood that the present invention has been described merely by way of example and that modifications of detail can be made within the scope of the invention.

CLAIMS

1. A method of improving the efficiency with which fuel is burnt in a fuel burning apparatus and/or a method of reducing the emissions produced by a fuel which is burnt in a  
5 fuel burning apparatus, said method comprising dispersing an amount of at least one particulate lanthanide oxide in the fuel.
2. A method according to Claim 1 wherein the at least one lanthanide oxide comprises a lanthanide selected from the group consisting of cerium, lanthanum, neodymium and  
10 praseodymium.
3. A method according to Claims 1 or 2 wherein the at least one lanthanide oxide is  $\text{CeO}_2$ .
- 15 4. A method according to any one of the preceding Claims wherein the at least one lanthanide oxide has a particle size in the range of 1 to 50 nm.
5. A method according to any one of the preceding Claims wherein the at least one lanthanide oxide is made by plasma vapour synthesis or mechanical chemical processing.  
20
6. A method according to any one of the preceding Claims wherein the at least one lanthanide oxide is coated with a substance which renders the surface of the lanthanide oxide lipophilic.
- 25 7. A method according to Claim 6 wherein the substance which coats the lanthanide oxide is a surfactant having an HLB of 7 or less.
8. A method according to Claims 6 or 7 wherein the substance which coats the lanthanide oxide is oleic acid or dodeceny succinic anhydride.  
30
9. A tablet suitable for dispersion of at least one lanthanide oxide in fuel comprising at least one lanthanide oxide as defined in any one of Claims 2 to 8 and a tableting aid which is dispersible in a fuel.

10. A tablet according to Claim 9 wherein the tableting aid is selected from the group consisting of a C<sub>7</sub>-C<sub>30</sub> alkyl carboxylic acid, a C<sub>6</sub>-C<sub>30</sub> aromatic compound, and polymeric tableting aids.
- 5 11. A tablet according to Claim 10 wherein the tableting aid is tetradecanoic acid.
12. A tablet according to any one of Claims 9 to 11 wherein the amount of lanthanide oxide is in the range of 1 to 99.99 wt. %, based on the total weight of the tablet.
- 10 13. A tablet according to any one of Claims 9 to 12 wherein the amount of tableting aid is in the range of 0.01 to 99 wt. %, based on the total weight of the tablet.
14. A method for producing a tablet according to any one of Claims 9 to 13 comprising  
15 the steps of preparing a composition comprising a lanthanide oxide as defined in any one of Claims 2 to 8 and a tableting aid as defined in any one of Claims 9 to 11 and applying a direct compression force to said composition.
15. A composition comprising a lanthanide oxide as defined in any one of Claims 2 to  
20 8 and a tableting aid as defined in any one of Claims 9 to 11.
16. A capsule suitable for dispersion of at least one lanthanide oxide in fuel comprising an outer case and a substance contained therein, wherein the outer case comprises at least one tableting aid as defined in any one of Claims 9 to 11 and the substance contained  
25 therein comprises at least one lanthanide oxide as defined in any one of Claims 2 to 8.
17. A liquid fuel additive suitable for dispersion of at least one lanthanide oxide in fuel comprising a dispersion of at least one lanthanide oxide as defined in any one of Claims 4 to 8 in an organic liquid medium.
- 30 18. A method according to any one of Claims 1 to 8 wherein the fuel burning apparatus is an internal combustion engine.

19. A method according to Claim 18 wherein the lanthanide oxide which is dispersed in the fuel is in the form of a tablet according to any one of Claims 9 to 13, a capsule according to Claim 16 or a liquid fuel additive according to Claim 17.
- 5 20. A method according to Claim 19 wherein the amount of tablet, capsule or liquid fuel additive dispersed in the fuel is such that the concentration of lanthanide oxide in the fuel is in the range of 1 to 10 ppm.
21. An apparatus comprising an internal combustion engine and a fuel system, wherein  
10 said fuel system comprises a fuel tank containing fuel, and means for delivering said fuel from said fuel tank to said internal combustion engine, characterised in that said fuel has at least one lanthanide oxide as defined in any one of Claims 2 to 8 dispersed therein.



(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
3 January 2002 (03.01.2002)

PCT

(10) International Publication Number  
WO 02/000812 A3

- (51) International Patent Classification<sup>7</sup>: C10L 1/12, 1/10, 10/02, 10/00, 10/04
- (21) International Application Number: PCT/GB01/02911
- (22) International Filing Date: 29 June 2001 (29.06.2001)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:  
0016032.5 29 June 2000 (29.06.2000) GB  
0022449.3 13 September 2000 (13.09.2000) GB
- (71) Applicant (*for all designated States except US*):  
NEUFTEC LIMITED [DM/DM]; 42 Kennedy Avenue, Roseau, Commonwealth of Dominica, West Indies (DM).
- (72) Inventors; and
- (75) Inventors/Applicants (*for US only*): HAZARIKA, Romen [GB/GB]; P.O. Box 4260, Poole BH13 7YS (GB). MORGAN, Bryan, Lawrence [GB/GB]; P.O. Box 4260, Poole BH13 7YS (GB).
- (74) Agents: FISHER, Adrian, John et al.; Carpmals & Ransford, 43 Bloomsbury Square, London WC1A 2RA (GB).
- (81) Designated States (*national*): AE, AG, AI, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
- Published:  
— with international search report
- (88) Date of publication of the international search report:  
12 September 2002
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: A FUEL ADDITIVE

(57) Abstract: This invention relates to a method for improving the efficiency with which fuel is burnt in a fuel burning apparatus, particularly an internal combustion engine, comprising dispersing an amount of at least one particulate lanthanide oxide, particularly cerium oxide, in the fuel. This invention further relates to tablets, capsules, compositions and liquid fuel additives suitable for dispersing a lanthanide oxide in fuel.

## INTERNATIONAL SEARCH REPORT

International Application No.

ru/GB 01/02911

A. CLASSIFICATION OF SUBJECT MATTER		
IPC 7 C10L1/12	C10L1/10	C10L10/02 C10L10/00 C10L10/04
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED		
Minimum documentation searched (classification system followed by classification symbols)		
IPC 7 C10L		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used)		
EPO-Internal		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with Indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 671 205 A (RHONE POULENC CHIMIE) 13 September 1995 (1995-09-13) the whole document	1-8, 17, 18, 20, 21
X	EP 0 575 189 A (RHONE POULENC CHEMICALS) 22 December 1993 (1993-12-22) the whole document	1-7, 17, 18, 20, 21
X	GB 1 005 957 A (CARBORUNDUM CO) 29 September 1965 (1965-09-29) page 2; claims 1, 11, 19, 21, 27 page 5	1-4, 6, 7, 17, 20
X	EP 0 599 717 A (RHONE POULENC CHIMIE) 1 June 1994 (1994-06-01) the whole document	1-8, 17, 18, 21
	--- -/-	
<input checked="" type="checkbox"/>	Further documents are listed in the continuation of box C.	
<input checked="" type="checkbox"/>	Patent family members are listed in annex.	
<p>* Special categories of cited documents:</p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubt on priority claim(s) or which is cited to establish the publication date of another claim or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</p> <p>"Z" document member of the same patent family</p>		
Date of the actual completion of the international search		Date of mailing of the international search report
7 June 2002		21/06/2002
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentkan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl Fax: (+31-70) 340-3318		Authorized officer  De La Morinerie, B

## INTERNATIONAL SEARCH REPORT

International Application No  
r.c.i./GB 01/02911

C/(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P, X	WO 00 49098 A (CHANE CHING JEAN YVES ; RHONE POULENC CHIMIE (FR)) 24 August 2000 (2000-08-24) the whole document ---	1-8, 17, 18, 20, 21
X	WO 99 13026 A (BLANCHARD GILBERT ; BIRCHEM THIERRY (FR); RHONE POULENC CHIMIE (FR)) 18 March 1999 (1999-03-18) the whole document ---	1-8, 17, 18, 20, 21
X	FR 734 135 A (LUBOVITCH EUGENE) 17 October 1932 (1932-10-17) the whole document ---	1, 2
A	EP 0 794 004 A (MONTECATINI TECNOLOGIE SRL) 10 September 1997 (1997-09-10) page 5, line 26 - page 6, line 7 ---	9-15
A	US 2 402 854 A (THOMAS CHARLES L) 25 June 1946 (1946-06-25) the whole document ---	9-15
A	DATABASE WPI Section Ch, Week 199306 Derwent Publications Ltd., London, GB; Class H06, AN 1993-049214 XP002201591 & JP 05 000243 A (KAWASAKI H), 8 January 1993 (1993-01-08) abstract ---	9
A	DE 197 01 961 A (METZ ADOLF DIPL CHEM) 24 December 1998 (1998-12-24) the whole document ---	1
A	WO 98 04655 A (DEN NESTE CORINNE VAN ; BRIARD GERARD (FR); BRISSET GUY (FR); PEYRO) 5 February 1998 (1998-02-05) cited in the application -----	

## INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No.

PCT/GB 01/02911

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0671205	A	13-09-1995	FR 2716388 A1	25-08-1995
			FR 2726199 A1	03-05-1996
			AT 192352 T	15-05-2000
			AU 698799 B2	05-11-1998
			AU 1231795 A	31-08-1995
			BR 9500667 A	24-10-1995
			CA 2142931 A1	19-08-1995
			CN 1115262 A	24-01-1996
			DE 69516569 D1	08-06-2000
			DE 69516569 T2	04-01-2001
			DK 671205 T3	07-08-2000
			EP 0671205 A2	13-09-1995
			ES 2145879 T3	16-07-2000
			GR 3033992 T3	30-11-2000
			HU 70898 A2	28-11-1995
			JP 7284651 A	31-10-1995
EP 0575189	A	22-12-1993	AT 149993 T	15-03-1997
			AU 4133293 A	23-12-1993
			AU 678925 B2	12-06-1997
			AU 4335596 A	26-04-1996
			BR 9302397 A	11-01-1994
			CA 2098666 A1	18-12-1993
			CN 1085905 A ,B	27-04-1994
			DE 69308651 D1	17-04-1997
			DE 69308651 T2	24-07-1997
			DK 575189 T3	08-09-1997
			EP 0575189 A1	22-12-1993
			ES 2101953 T3	16-07-1997
			FI 932794 A	18-12-1993
			GR 3023445 T3	29-08-1997
			HU 65458 A2	28-06-1994
			JP 6056850 A	01-03-1994
			MX 9303631 A1	31-01-1994
			NO 932232 A ,B,	20-12-1993
			US 5449387 A	12-09-1995
			US 5674985 A	07-10-1997
GB 1005957	A	29-09-1965	US 3205053 A	07-09-1965
			US 3231592 A	25-01-1966
			FR 1325217 A	26-04-1963
			NL 278128 A	
EP 0599717	A	01-06-1994	FR 2698346 A1	27-05-1994
			AT 179960 T	15-05-1999
			AU 672834 B2	17-10-1996
			AU 5191793 A	16-06-1994
			BR 9304813 A	31-05-1994
			CA 2109887 A1	26-05-1994
			CN 1091768 A ,B	07-09-1994
			DE 69324890 D1	17-06-1999
			DE 69324890 T2	18-11-1999
			EP 0599717 A1	01-06-1994
			ES 2133371 T3	16-09-1999
			GR 3030800 T3	30-11-1999
			HU 69749 A2	28-09-1995
			JP 2858624 B2	17-02-1999
			JP 6340418 A	13-12-1994

## INTERNATIONAL SEARCH REPORT

Information on patent family members

 International Application No  
 PCT/GB 01/02911

Patent document cited in search report		Publication date		Patent family member(s)		Publication date
EP 0599717	A		KR	9709568 B1		14-06-1997
			MX	9307312 A1		31-05-1994
			US	6093223 A		25-07-2000
WO 0049098	A	24-08-2000	FR	2789601 A1		18-08-2000
			BR	0008339 A		29-01-2002
			CN	1346391 T		24-04-2002
			EP	1157071 A1		28-11-2001
			WO	0049098 A1		24-08-2000
			NO	20014029 A		17-10-2001
WO 9913026	A	18-03-1999	FR	2768155 A1		12-03-1999
			AU	9078898 A		29-03-1999
			BR	9812072 A		26-09-2000
			CA	2303137 A1		18-03-1999
			CN	1275158 T		29-11-2000
			EP	1019462 A1		19-07-2000
			WO	9913026 A1		18-03-1999
			HU	0004601 A2		28-04-2001
			JP	2001515946 T		25-09-2001
			NO	20001237 A		10-05-2000
FR 734135	A	17-10-1932	NONE			
EP 0794004	A	10-09-1997	IT	MI960447 A1		08-09-1997
			AU	716285 B2		24-02-2000
			AU	1510397 A		11-09-1997
			BR	9701231 A		25-08-1998
			CA	2199218 A1		08-09-1997
			CZ	9700650 A3		17-09-1997
			EP	0794004 A1		10-09-1997
			HR	970129 A1		30-04-1998
			HU	9700554 A2		02-03-1998
			JP	10000359 A		06-01-1998
			NO	971062 A		09-09-1997
			PL	318846 A1		15-09-1997
			RU	2167711 C2		27-05-2001
			SK	30497 A3		10-09-1997
			TW	444003 B		01-07-2001
			US	6166280 A		26-12-2000
US 2402854	A	25-06-1946	NONE			
JP 5000243	A	08-01-1993	NONE			
DE 19701961	A	24-12-1998	DE	19701961 A1		24-12-1998
WO 9804655	A	05-02-1998	FR	2751662 A1		30-01-1998
			CN	1228802 A		15-09-1999
			EP	0946681 A1		06-10-1999
			WO	9804655 A1		05-02-1998
			JP	2000515917 T		28-11-2000
			US	6096104 A		01-08-2000